

Product Details

Franciscusweg 219m NL 1216SE
Hilversum, Netherlands

PHONE +31-35-5239152

Unireservoir DL-2T

Manufacturer

Kyodo Yushi

Remarks

Timken OK load ASTM D 2509 : 20.4kg

Grease cartridge (GKL-2-50 or GKL-2-100)

temperature range

-30 °C <—> 130 °C

Characteristics	Test Method	Typical
Type of base oil	--	mineral N.A.
Thickener	--	lithium
Base oil viscosity		
@ 40 °C	ISO 3104	170
@ 100 °C mm ² /s	DIN 51562	12.5
Appearance	--	yellow brown
NLGI Class	DIN 51818	2
Worked penetration	ISO 2137	280
Dropping point, °C	ISO 2176	200
Copper strip corrosion 24h/100°C	ASTM D 4048	OK
Evaporation loss (99°C, 22h), %	ASTM D 972 IP 183	
Oil separation 100 °C 24h	FTMS 791B321 mod.	2.2
Oxidation stability, kPa 100h/99°C	ASTM D 942	
Low temp.torque °C	ASTM D 1478-63	starting
N·cm		running
4-Ball weld load (N)		W.P.
Corrosion protection	ASTM D 1743	1
Water washout, 1hr at 79°C	ASTM D 1264	
Water resistance	°C	