

# \* PRODUCT INFORMATION \*

## **HUSKEY™ 350 SILICONE GREASE**

### **DESCRIPTION**

**HUSKEY 350 SILICONE GREASE** is a non-hardening and non-carbonizing silicone lubricant with excellent dielectric properties, plus both physical and thermal stability. **HUSKEY 350 SILICONE GREASE** is insoluble in water, methanol, ethanol, dilute acids and caustics, vegetable and mineral oils, glycol and glycerin. A **USDA/NSF H-1 Registration** permits use of **HUSKEY 350 SILICONE GREASE** in applications where there may be incidental food contact.

**USAGE.** The long service life and chemical resistance of **HUSKEY 350 SILICONE GREASE** makes it an excellent lubricant and sealant for many valves including plug, pressure, vacuum and control. **HUSKEY 350 SILICONE GREASE** is a very effective lubricant for O-rings and other rubber or plastic applications. It is excellent for applications that require temperature and mechanical stability which include fire extinguisher, water faucet valves, water softener valves, lock mechanisms, flow meter bearings, electrical assemblies and terminals, etc.

### **ADVANTAGES**

- **HIGH DIELECTRIC STRENGTH**
- **WATERPROOF, WILL NOT WASH OUT**
- **NSF H-1 Registered (No. 122830) and KOSHER Approved**
- **STABLE CONSISTENCY -55°F TO 570°F**
- **CHEMICAL RESISTANT**
- **EXTREMELY LOW VOLATILITY**
- **MEETS MIL-S-8660C SPECIFICATIONS**
- **COMPATIBLE WITH COMMON RUBBERS AND PLASTICS**

### **TYPICAL PROPERTIES**

Base Oil	Polydimethylsilicone
Color	Translucent White
N.L.G.I. Grade	3
Penetration (ASTM D-217)	220-250
Flash Point, °F (ASTM D-92)	570
Dropping Point, °F (ASTM D-566)	None
Pour Point, °F (ASTM D-97)	-55
Water Washout, % (ASTM D-1264)	0.25
Dielectric Strength, @ 25°C, volts/mil	800
Specific Gravity, @ 25°C	0.97



### **PACKAGE AVAILABILITY**

1 gal. Pails, 5 gal. Pails, 15 gal. Kegs and 55 gal Drums  
Custom Packaging Available on Request



The name of this product or group of products is for product identification purpose only. *HUSK-ITT Corporation* makes no warranties, representations or conditions of any kind express or implied, whether for merchantability or fitness for use with respect to these products. The final determination of the suitability of the products for the application contemplated by the user is the sole responsibility of the buyer. *HUSK-ITT Corporation* sales personnel are not authorized to amend this warranty limitation. 11/10



## **HUSKEY Specialty Lubricants**

manufactured by *HUSK-ITT Corporation* / *SPECIALTY LUBRICANTS Corporation*

### **Western Region Office:**

1580 Industrial Avenue, Norco, California 92860  
(951) 340-4000 • Fax: (951) 340-4011  
(888) 4-HUSKEY • [www.huskey.com](http://www.huskey.com)

### **Eastern Region Office:**

8300 Corporate Park Drive, Macedonia, Ohio 44056  
(330) 425-2567 • Fax: (330) 425-9637  
(800) 238-LUBE