

Castrol Optitemp HT 1LF NG

Grease for CV joints subjected to extremely high thermal and mechanical loads

Description

CASTROL OPTITEMP™ HT 1 LF NG is a grease which has been designed for the most extreme loads in constant velocity ball joints. It features excellent high and low temperature behavior and due to its special additives guarantees a reduction of the coefficient of friction resulting in reduced fuel consumption and lowered temperatures in the joints. It is also recommended for the application with ventilated boots due to extremely low evaporation losses. The compatibility with boots made of commonly used materials is very good.

Application

- Application in homokinetic ball joints
- Vehicles which require „Fuel Economy“
- Joints subjected to extremely high mechanical and thermal loads
- Application at extreme temperatures (- 45°C/- 49°F):
 - 45°C/- 49°F low temperature application
 - 160°C/320°F permanent temperature application
 - 180°C/356°F maximum temperature application

Advantages

- wide temperature range
- long service life
- extremely low coefficients of friction
- very good oxidation stability
- optimum boot compatibility with CR and Hytrel
- „Fuel Economy“ (in extreme cases up to 0.15 l / 100 km)
- lowering of joint temperatures generated by friction
- extraordinarily low evaporation losses

Typical Characteristics

Test	Method	Unit	Value
CASTROL OPTITEMP	-	-	HT 1 LF
Colour	visual	-	black
Base	-	-	polyurea/fully synthetic
Worked penetration Pw 60	DIN ISO 2137	0.1 mm	310
Density at + 20°C/+ 68°F	DIN 51757	kg/m ³	890
Base oil viscosity at + 40°C/+ 104°F	DIN 51562	mm ² /s	303
Dropping point	DIN ISO 2176	°C	> 230
		°F	> 446
Water resistance at + 90°C/+ 194°F	DIN 51807 T. 1	-	0
Corrosion protection (SKF Emcor)	DIN 51802	-	0
Flow pressure at + 20°C/+ 68°F at - 20°C/- 4°F at - 35°C/- 31°F	DIN 51805	mbar	85
			350
			1400
VW oil separation (1h/+ 90°C/+ 194°F)	-	%	< 4.0
Seal compatibility: Inepsa CR 4012 (168h/+ 100°C/+212°F):	DIN 53505 DIN 53521	Shore	+ 4 - 4
Change in hardness		%	
Change in volume		%	

1 mm²/s $\hat{=}$ 1cSt

Subject to usual manufacturing tolerances

Additional Information

CASTROL OPTITEMP HT 1 LF NG is compatible with the elastomers chloroprene rubber (CR) and polyetherester rubber (Hytrel)

Castrol, Optitemp, and the Castrol logo are trademarks of Castrol Limited, used under licence

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Limited, Pipers Way, Swindon, Wiltshire SN3 1RE, UK
www.castrol.com/industrial
www.castrol.com/industrial